


The effect on traction of adding Priolube™ EF 3446 to Group III and Group IV base oils



Parameter	Value
Speed	2 m/s
Temperature	40°C
Load	16N
SRR	0-100%

In Group III, adding 20% Priolube™ EF 3446 reduces traction by an average of 26% across the complete slide roll ratio vs untreated Group III

In Group IV, the average reduction is 11%.